

FLORQUARTZ BC

DECORATIVE EPOXY SCREED MORTAR WITH MULTI COLOUR GRANULES

Product Description

FLORQUARTZ BC is based on carefully selected solventless Epoxy resin composition. It is a three component system consisting of base, hardener and hard wearing colour quartz. It is a self levelling composition and forms an anti-slip, attractive, hygienic, hard wearing and chemical resistant floor topping.

Green Building Compliance

This product has following distinct advantages

- Eco-friendly
- Low VOC
- Solvent free with a high level of mechanical, chemical and water resistance,
- Low odour
- Antimicrobial
- Low maintenance
- Easier cleanability
- LEED compliant
- Ideal for use in Green Building

Features

Hygienic-It provides jointless flooring making it dust free and is easy to clean because of smooth surface.

Chemical Resistant – It has excellent chemical resistance to most chemicals

Wear Resistant- It provides a tough floor topping to withstand foot and light vehicular traffic.

Aesthetics-It is available in various colour shades to provide attractive floor finish.

Uses

FLORQUARTZ BC is recommended for use where extremely hygienic, abrasion, chemical resistant and dust free environment is required. It is ideally suited for following industries.

- Beverage Industry
- Food Courts
- Airport Kitchen
- Food Processing industries
- Meat processing areas

Properties

| | |
|---|--------------------|
| Average Thickness | : 3-5 mm |
| Finish | : Gloss/Semi Gloss |
| Pot Life @ 30°C | : 25-30 mins |
| Compressive strength (ASTM C 579) | : > 65 MPa |
| Flexural strength (ASTM C 580) | : > 35 MPa |
| Tensile strength (ASTM C 307) | : > 25 MPa |
| Bond strength to concrete (ASTM D 4541) : (Elcomete pull of test) Exceeds Tensile strength of concrete | |
| Hardness, Shore D (ASTM D 2240) | : >80 |
| Curing Time | : |
| Initial Cure | 6 hours, |
| Full Mech. Cure | 48 hours |
| Ready for use | To walk – 24hrs |
| To light traffic | 48 hrs |
| Full Chemical Cure | 7 days |
| Mixing Ratio | - As supplied. |

The values given above are average figures achieved in laboratory tests. Actual values obtained on site may show minor variations from those quoted.

Coverage/Consumption

FLORQUARTZ BCU : 1.2kg /sqm for 3 mm thickness

FLORQUARTZ BCT : 4kg/sqm for 3mm thickness

System Information

FLORQUARTZ BC system @ 3 mm is as follows:

| Coating System | Product | Consumption |
|---------------------------------|------------------------------------|------------------------|
| Primer | Florprime EP | 0.2 kg/m ² |
| Base coat FLORQUARTZ BCU 250 | (Base , Curing agent & aggregates) | 1.2 kg/m ² |
| Top coat FLORQUARTZ BCT | Colour Quartz for broadcast | 3.0 kg/m ² |
| | FLORQUARTZ BCT for sealcoat | 1.00 kg/m ² |

FLORQUARTZ BC system @ 4.5mm is as follows:

| Coating System | Product | Consumption |
|--------------------------------------|--------------------------------|------------------------|
| Primer | Florprime EP | 0.2 kg/m ² |
| Base Coat 1 | FLORGARD SL 1000 | 1.2 kg/m ² |
| Base coat 2 FLORQUARTZ BCU 450 | Aggregates Broadcast 26 | 3.0 kg/m ² |
| | FLORQUARTZ BCU 450 | 0.8 kg/m ² |
| Top coat FLORQUARTZ BCT | Colour Quartz for broadcast | 3.0 kg/m ² |
| | FLORQUARTZ BCT for sealcoat | 1.00 kg/m ² |

Method of Application

APURVA's system should be installed by approved contractors. Following information should be used as a guideline

Inspection and Surface preparation

The long term durability of the applied **FLORQUARTZ BC** topping is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surface is correctly prepared prior to application.

1. New concrete or cementitious substrates should have been placed for at least 28days and have a moisture content of less than 5% before topping with **FLORQUARTZ BC**.
2. Before application, the surface to be coated should be free from loose particles, rust, oils, grease or earlier coatings and should be thoroughly dry.
3. After surface is dry, all repair work like sealing of joints, cracks filling of cavities and crevices should be carried out.
4. The self levelling action is very localised and does not eradicate irregularities of level present in the original substrate. It is most important, therefore, that adequate surface preparation and repair is undertaken prior to application of **FLORQUARTZ BC** flooring systems.

Concrete defects such as voids, bug holes, excess porosity, and physical and chemical damage are usually filled or repaired prior to the installation of the F/C system. (Materials such as slurries, mortars, and polymer concrete are used to level, smooth and patch concrete surfaces).

The laitance (A thin, weak, brittle layer of cement and aggregate on concrete surface) on in-situ bases and any surface sealer or curing membrane should be entirely removed by suitable mechanised equipment, e.g. shot-blasting, panning or grinding, to expose cleanly the coarse aggregate.

Old Concrete surfaces: All surface contamination, e.g. oil, paint and rubber, should be removed and adequate mechanical preparation carried out to achieve a sound and stable surface with exposed coarse aggregate. (Existing floor paints should be removed by mechanical abrasion or contained shot blasting. When clear of all surface contamination, the concrete should be prepared mechanically to remove all laitance and expose a fresh surface).

After surface preparation all loose debris and dirt should be removed by vacuum- equipment.

Priming:

For use over a concrete surface, **FLORPRIME WB / FLORPRIME EP** primer is recommended depending on substrate condition to ensure maximum product performance.

Laying of FLORQUARTZ BC

FLORQUARTZ BC shall be mixed and applied only by specialist flooring contractors who have been trained in the correct application procedures. Detailed method of statement is available on request.

Mixing:

A) For Base coat :
Pack components are pre-weighed for optimum performance. Never split packs. Empty contents of Base into a mixing container and pre-mix to assure the suspension of solids. Add Curing Agent and continue to mix to a uniform consistency for 1-2 minutes. Add the quantity of aggregates supplied and mix for 1-2 minutes. Mix with slow speed drill and helical spinner head for 2 minutes. Avoid high speed mixing that will entrain air into the mix.

B) For Top coat :
Pack components are pre-weighed for optimum performance. Never split packs. Empty contents of Base into a mixing container and pre-mix to assure the suspension of solids. Add Curing Agent and continue to mix to a uniform consistency for 1-2 minutes. Mix with slow speed drill and helical spinner head for 2 minutes. Avoid high speed mixing that will entrain air into the mix.

Special conditions

Colours

We shall always endeavour to supply the material in the colour shade ordered. However exact matching will not be possible.

Batch to batch colour variation may occur. Ensure that materials for final application are always drawn from the same batch.

Where colour matching is required over more than one order or delivery. Apurva's Technical department must be contacted prior to placing the order(s) and the requirement stated clearly on all orders relating to the project(s).

Substrate Requirements

- Must be of sufficient strength to support loads applied through the topping.
- Must be free from rising damp.
- All contamination must be removed to give a clean dry textured surface.

Substrate Movements

All moving joints must be carried through the **FLORQUARTZ BC** and properly sealed. Construction joints and cracks may be covered but if substrate movement occurs, the **FLORQUARTZ BC** will reflect the crack.

Repairs & Levels

Concrete floors are generally laid to a levels tolerance of +/- 3mm under a 3 metre straight edge. Whilst **FLORQUARTZ BC** has excellent local levelling properties, overall level deviations will not be eliminated by laying a self smoothing topping of 2-3mm.

When applied on old floors, all damaged areas of the floor should be made good and upto level using epoxy mortar.

Packaging

FLORQUARTZ BCU 250 12kg

FLORQUARTZ BCU 450 31kg

FLORQUARTZ BCT 42kg

Shelf life

FLORQUARTZ BC has a shelf life of 12 months if kept in warehouse conditions at 30°C in the original, unopened pack.

Storage conditions

Store in dry conditions between 5°C and 30°C, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures the shelf life will be reduced

Handling & Safety

Keep the containers tightly sealed when not in use. Avoid skin contact and inhalation of fumes (if any). While spraying it is advised to wear a mask. If it comes in contact with the body, wash affected parts with plenty of water. In case of persistent irritation, contact a physician.

Disclaimer: *The manufacturer reserves the right to change the specifications. Apurva India Private Limited products are guaranteed against material manufactured and are sold subject to the company's Terms and Conditions of Sale. Whilst we endeavour to ensure that advice, specifications, recommendations and information given is correct, we cannot have control over how our products are applied and will not accept liability, directly or indirectly, arising from application of our materials.*

Version No./Date of revision : 04/July 2017

APURVA INDIA PRIVATE LIMITED

New Udyog Mandir No. 2, Office No. 2, 2nd Floor, 7C Pitambar Lane, Mahim (W), Mumbai 400 016, India.
Tel: +91-22-24475051 (5 Lines) | Fax: +91-22-24475056 | Website: www.apurvaindia.in

